

YU-TP21 AMERICAS

BEST VALUE IN THE WORLD OF CUTTING TOOLS



FOR TITANIUM, STAINLESS STEELS AND ALLOY STEELS :
TOUGH MATERIALS
TAKE IT ON WITH TITANOX

TitaNox Power

INDUSTRY-LEADING SOLID CARBIDE END MILLS




HIGH-PERFORMANCE
MACHINING MADE EASY:

- Variable Helix and Pitch
- 4 Flute and 5 Flute
- Square End, Chamfer and Radius
- Standard and Extended Lengths
- Inch and Metric Sizes
- 5 Flute Heavy Cutting Solution
TitaNox Power HPC **NEW**

Take It On With

TitaNox Power

HIGH-PERFORMANCE MACHINING MADE EASY.

-  Titanium
-  Stainless Steels
-  Alloy Steels



If you've been looking for a superior carbide end mill that won't back down when the going gets tough, it's time you look at TitaNox.

The TitaNox line is built to take on titanium, stainless steels, alloy steels, and more. With a choice of 4- and 5 flute designs and extra-rigid high-speed performance, TitaNox makes the perfect match for aerospace, power generation and medical applications.

TitaNox — Nothing Cuts Better.

With more choices in high-performance carbide end mills, YG-1 is the undisputed leader in end mill offerings. And with the TitaNox line, you have a full selection of extremely durable end mills built to take on the toughest materials in the business. From titanium to stainless steel and more—TitaNox rules. In either 4 flute or 5 flute configurations you get:

- ▶ YG-1 advanced coating for better wear resistance
- ▶ Better thermal stability
- ▶ Optimized edge design provides excellent performance in heavy cutting applications
- ▶ Excellent performance in difficult-to-machine materials
- ▶ Perfect solution for aerospace, power generation and medical applications
- ▶ Premium grade substrate for longer tool life

**TitaNox Power
4 FLUTE DOUBLE CORE END MILLS**



Let the Chips Fly.

For heavy cutting in slotting and profiling applications, our true double-core design provides faster chip evacuation and improved dimensional stability. Experience what a difference double-core design can make in your operation.

- ▶ Highly rigid double core adds stability and improves rigidity
- ▶ Unique 4 flute design provides excellent chip evacuation
- ▶ Variable flute design featuring multiple helix helps increase performance, reduce vibration and eliminate chatter

**TitaNox Power
5 FLUTE MULTIPLE HELIX END MILLS**




**Strong Performance —
Right to the Finish.**


These new 5 flute end mills are built to handle high-speed machining with fine finishing ability.

- ▶ 5 flute multiple helix design for fast, fine finishing in tough materials
- ▶ Multiple-helix geometry delivers smooth cutting with reduced chatter
- ▶ The perfect choice for profiling, finishing, peel milling operations and more
- ▶ New HPC Solution for Heavy Cutting Applications


CASE STUDY


4 Flute Double Core End Mills vs. Competitors

Cutting Conditions	
Milling Method	Slotting 
Work Material	- DIN : Ti6Al4V (Titanium) - WR : 3.7165.1
Size	Ø12(R1) x Ø12 x 26 x 80
RPM	1591 rev./min.
IPM	10 in./min.
Axial Depth	.470"
Coolant	Wet Cut
Overhang	1.41"
Machine	Machining Center






5 Flute Multiple Helix End Mills vs. Competitors

Cutting Conditions	
Milling Method	Down & Side Cutting 
Work Material	- DIN : Ti6Al4V (Titanium) - WR : 3.7165.1
Size	Ø12 x Ø12 x 26 x 83
RPM	1591 rev./min.
IPM	15.669 in./min.
Axial Depth	.710"
Radial Depth	.141"
Coolant	Wet Cut
Machine	Machining Center




5 Flute TitaNox Power HPC vs. Competitor

Cutting Conditions	
Milling Method	Side Cutting 
Work Material	- DIN : Ti6Al4V (Titanium) - WR : 3.7165.1
Size	3/4(R.03")x3/4x1-1/2x4"
RPM	2000 rev./min.
IPM	30 in./min.
Milling Method	Axial : .075" / Radial : 1.5"
Coolant	Wet Cut
Machine	Machining Center




How Our 4-Flute Double-Core Design Can Cut It Where Others Can't.


Whether in profiling or slotting conditions, the TitaNox double-core design takes end milling titanium and other tough metals to a new level. With our super-rigid, heat resistant design featuring an innovative large gullet configuration, the TitaNox can cut it where single-core designs can't. With outstanding chip evacuation and the added ability to maneuver in tough materials, the TitaNox double-core end mills can combine heavy profiling and slotting in the same move—without vibration or chip packing.




▲ Thin-core designs allow aggressive cutting at first, but are soon slowed down due to excessive vibration, and often break.



▲ Thick-core designs provide enhanced stability but don't deliver enough chip evacuation, which can often lead to catastrophic failure.



▲ The TitaNox double-core design provides the best of both worlds – excellent chip evacuation combined with tool rigidity—to ensure stability, cut after cut. All this, plus quiet, vibration-free operation.




▲ The illustration above detailed along the X-X' axis shows how the 4 flute design starts the cut with aggressive chip evacuation. The Y-Y' axis shows how the double core comes into play, providing perfect slotting operations through its extra-rigid double-core design.


Super-Stable, Super-Performing, Super-Productive.




▲ For smooth, effortless profiling, the double-core design provides extremely stable cutting for increased productivity. No other end mill performs better in tough cutting conditions.



▲ Switch from profiling to slotting without excessive vibration without loading up. TitaNox double-core design pushes productivity higher in tough-to-mill materials.



▲ Other 4 flute single-core tools can load up in heavy axial depths of cut and break, as shown in the illustration above.



▲ The TitaNox super-rigid design and large gullet configuration provide excellent chip evacuation in titanium.

Customized End Mills!

Now the best value in the world of cutting tools goes one better with the **YG-1 QuickTurn Special End Mill Program**.

Get customized solid carbide end mills for your specific application plus, quick response specials – LOC, radius and LBS, all with YG-1's advanced technology and the high-performance cutting-edge features of **V7 PLUS A** and **TitaNox-Power** end mills.

And since your order goes to our state-of-the-art Tech Center in Charlotte, NC right here in the USA, it goes into production the same day.

We're known for bringing you the widest standard end mill offering in the industry.

With our new QuickTurn program, the possibilities are almost unlimited!

V7 PLUS A




TitaNox-Power



Our Advanced Coating cuts faster—and lasts longer.


Compared to other competitive coatings currently on the market, YG-1's new advanced coating brings you the best of both worlds — increased tool hardness and higher speed performance. It all adds up to increased productivity in tough materials, and longer tool life. But what really sets our advanced coating apart is how it makes the TitaNox line the best value around in cutting tools — just another way YG-1 adds more value for less.



NEW
TitaNox Power HPC
 NEW 5 FLUTE DESIGN for
HEAVY CUTTING APPLICATIONS
 SLOTTING & HIGH EFFICIENCY MILLING


Features

- New design enhances chip space in heavy cuts, while still maintaining rigidity in peel milling.
- Full eccentric relief for edge strength.
- YG-1 advanced coating for better wear resistance
- Unequal index design for Chatter-Free cutting



Unequal Index

Exclusively Designed Unique Geometry applied to Reduce Vibration and also to achieve Excellent surface finish




38° Single Helix

Core Design

YG-1's High Performance Core Geometries is designed for superior chip evacuation. It's excellent at Slotting & Heavy Profiling.

Applications




Work Materials



Recommended for high performance milling of Stainless Steel, Titanium, and Heat-Resistant Super Alloys

CASE STUDY




Part Description
Hydraulic Valve

Size(inch)	1/2(R.03") x 1/2 x 1-1/4 x 3-1/2
Work Material	15-5PH (HRc 34-42 / HB 320-400)
Tool Holder	Shrink fit
SFM	420 ft/min.
IPM	80 inch/min.
RPM	3,200 rev./min.
Milling Method	Trochoidal Cutting
Ap	1.000"
Ae	.025"
Coolant	Water-Based
Machine	Machining Center

14 Parts
YG



7 Parts
 Competitor A



Part Description
Aerospace Structure part

Size(inch)	5/8(R.12") x 5/8 x 1-1/2(2") x 4"
Work Material	Ti6Al4V (HRc 36 / HB 336)
Tool Holder	Shrink Fit
SFM	275-375 ft/min.
IPM	20-45 inch/min.
RPM	1680-2292 rev./min.
Milling Method	Helical Ramping, Pocket, Ramping, Profile and Slotting
Ap	.300" - 1.500"
Ae	.050" - .625"
Ramping	1° - 1-1/2°
Helical Interpolation	0.5°
Coolant	Water-Based
Machine	Machining Center

6-7 Hours
YG




3-4 Hours
 Competitor B

GUIDE TO ICONS


The tool is made of micrograin carbide




Helix Angle



Tool Ends:




Tool Ends:



No. of Flutes



Type of Shank




Cutting Conditions



HIGH PERFORMANCE SOLID CARBIDE END MILLS
4-FLUTE DOUBLE CORE STANDARD LENGTH (PLAIN SHANK)

SERIES
Corner Radius **UGMG42**

- ▶ Double core end mill has a unique flute design for excellent chip evacuation and higher rigidity.
- ▶ The double core adds stability and aids chip flow, reducing tool deflection, improving dimensional stability and workpiece accuracy.



Unit : INCH

OD (D1)	SD (D2)	LOC (L1)	OAL (L2)	Corner Radius								
				.010 EDP No.	.015 EDP No.	.030 EDP No.	.060 EDP No.	.090 EDP No.	.125 EDP No.	.190 EDP No.	.250 EDP No.	
1/4	1/4	9/16	2-1/2	UGMG42802	UGMG42016	UGMG42901	UGMG42902					
		3/4	2-1/2			UGMG42924	UGMG42925					
		1	3			UGMG425926*	UGMG425927*					
3/8	3/8	1/2	2-1/2			UGMG42K998	UGMG42K999	UGMG42K801				
		7/8	2-1/2			UGMG42928	UGMG42929	UGMG42930				
		13/16	2-1/2	UGMG42931		UGMG42905	UGMG42906	UGMG42907				
		1	3	UGMG42932	UGMG42803	UGMG42933	UGMG42934	UGMG42935				
1/2	1/2	1-1/4	3	UGMG425936*	UGMG42S804*	UGMG425937*	UGMG425938*	UGMG425939*				
		1	3	UGMG42940		UGMG42908	UGMG42909	UGMG42910	UGMG42911			
		1-1/4	3	UGMG42810	UGMG42811	UGMG42813	UGMG42815	UGMG42816	UGMG42817			
		1-1/4	3-1/2		UGMG42805	UGMG42912	UGMG42941	UGMG42942	UGMG42943			
5/8	5/8	1-1/4	3-1/2			UGMG42S944*	UGMG42S945*	UGMG42S946*	UGMG42S947*			
		1-5/8	4			UGMG42S806*	UGMG42S807*	UGMG42S808*	UGMG42S809*			
		2	4			UGMG42040	UGMG42913	UGMG42914	UGMG42915			
		1-1/4	3-1/2			UGMG42948	UGMG42949	UGMG42950	UGMG42951			
3/4	3/4	2	4			UGMG42S952*	UGMG42S953*	UGMG42S954*	UGMG42S955*			
		3-1/4	6			UGMG42S956*	UGMG42S957*	UGMG42S958*	UGMG42S959*			
		1-1/2	4			UGMG42048	UGMG42916	UGMG42917	UGMG42918	UGMG42919	UGMG42960	
		1-7/8	4			UGMG42961	UGMG42962	UGMG42963	UGMG42964	UGMG42965	UGMG42966	
1	1	2-1/4	5			UGMG42967	UGMG42968	UGMG42969	UGMG42970	UGMG42971	UGMG42972	
		3-1/4	6			UGMG42S973*	UGMG42S974*	UGMG42S975*	UGMG42S976*	UGMG42S977*	UGMG42S978*	
		2	5			UGMG42064	UGMG42920	UGMG42921	UGMG42922	UGMG42923	UGMG42979	
		2-5/8	5			UGMG42980	UGMG42981	UGMG42982	UGMG42983	UGMG42984	UGMG42985	
1	1	3	6			UGMG42986	UGMG42987	UGMG42988	UGMG42989	UGMG42990	UGMG42991	
		4-1/4	7			UGMG42S992*	UGMG42S993*	UGMG42S994*	UGMG42S995*	UGMG42S996*	UGMG42S997*	

Mill Dia. Tolerance (in) 0 ~ - .0012 Shank Dia. Tolerance h5 * Shank Dia. $\geq \phi 1/2$: h6
 * Length of cut in excess of 3x D on 45° single-helix requires feed reduction of approximately 50%
 © : Excellent ○ : Good


ISO Material Description	P										M				K					
	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel		Stainless steel		Grey cast iron	Nodular cast iron	Malleable cast iron			
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20
HRc	13	25	28	32	32	10	29	32	38	15	35	15	23	10	10	26	3	25	10	21
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250	130	230
Recommend	○	○	○	○	○	○	○	○	○	○	○	◎	◎	◎	○	○	○	○	○	○

ISO Material Description	N					S					H										
	Aluminum-wrought alloy		Aluminum-cast, alloyed		Copper and Copper Alloys (Bronze / Brass)	Non Metallic Materials		Heat Resistant Super Alloys			Titanium Alloys	Hardened steel	Chilled Cast Iron	Hardened Cast Iron							
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41
HRc											15	30	25	38	34	320	55	55	60	42	55
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550
Recommend	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	◎	◎	○	○	○	○

HIGH PERFORMANCE SOLID CARBIDE END MILLS
4-FLUTE STANDARD LENGTH (WELDON FLAT SHANK)

SERIES
Corner Radius **UGMG43**


- ▶ Double core end mill has a unique flute design for excellent chip evacuation and higher rigidity.
- ▶ The double core adds stability and aids chip flow, reducing tool deflection, improving dimensional stability and workpiece accuracy.



Unit : INCH

OD (D1)	SD (D2)	LOC (L1)	OAL (L2)	Corner Radius					
				.010 EDP No.	.030 EDP No.	.060 EDP No.	.090 EDP No.	.125 EDP No.	.190 EDP No.
3/8	3/8	13/16	2-1/2	UGMG43024	UGMG43905	UGMG43906	UGMG43907		
1/2	1/2	1	3		UGMG43908	UGMG43909	UGMG43910	UGMG43911	
		1-1/4	3		UGMG43926	UGMG43927	UGMG43928	UGMG43929	
		1-1/4	3-1/2		UGMG43912	UGMG43924	UGMG43930	UGMG43931	
5/8	5/8	1-1/4	3-1/2		UGMG43040	UGMG43913	UGMG43914	UGMG43915	
3/4	3/4	1-1/2	4		UGMG43048	UGMG43916	UGMG43917	UGMG43818	UGMG43919
1	1	2	5		UGMG43064	UGMG43920	UGMG43921	UGMG43922	UGMG43923

Mill Dia. Tolerance (in) 0 ~ - .0012 Shank Dia. Tolerance h5 * Shank Dia. $\geq \phi 1/2$: h6




ISO Material Description	P										M				K					
	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel		Stainless steel		Grey cast iron	Nodular cast iron	Malleable cast iron			
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20
HRc	13	25	28	32	32	10	29	32	38	15	35	15	23	10	10	26	3	25	10	21
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250	130	230
Recommend	○	○	○	○	○	○	○	○	○	○	○	◎	◎	◎	○	○	○	○	○	○

ISO Material Description	N					S					H										
	Aluminum-wrought alloy		Aluminum-cast, alloyed		Copper and Copper Alloys (Bronze / Brass)	Non Metallic Materials		Heat Resistant Super Alloys			Titanium Alloys	Hardened steel	Chilled Cast Iron	Hardened Cast Iron							
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41
HRc											15	30	25	38	34	320	55	55	60	42	55
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550
Recommend	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	◎	◎	○	○	○	○

HIGH PERFORMANCE SOLID CARBIDE END MILLS 5-FLUTE STANDARD LENGTH (PLAIN SHANK)

- Suitable for Titanium, Titanium Alloys, Inconel and Stainless Steels.
- Optimized flute design for chip evacuation and rigidity when machining difficult-to-cut materials.

- Special roughing profile for machining Titanium and Titanium Alloys.
- Longer tool life with special coating.



OD (D1)	SD (D2)	LOC (L1)	OAL (L2)	Corner Radius																		
				Square EDP No.	Chamfer EDP No.	.015					.030					.060	.090	.125				
						EDP No.					EDP No.					EDP No.	EDP No.	EDP No.				
1/8	1/8	1/4	1-1/2	UGMH12008	UGMG32008	UGMG34008	UGMG34950															
		3/8	1-1/2	UGMH12901	UGMG32901	UGMG34901	UGMG34951															
		1/2	2-1/2	UGMH12S902*		UGMG34S952*	UGMG34S953*															
		3/4	2-1/2	UGMH12S903*		UGMG34S954*	UGMG34S955*															
3/16	3/16	5/16	2	UGMH12012	UGMG32012	UGMG34012	UGMG34956															
		9/16	2	UGMH12904	UGMG32902	UGMG34902	UGMG34957															
		3/4	2-1/2	UGMH12S905*		UGMG34S958*	UGMG34S959*															
1/4	1/4	3/8	2	UGMH12016	UGMG32016	UGMG34960	UGMG34016	UGMG34961														
		1/2	2-1/2	UGMH12906		UGMG34962	UGMG34963	UGMG34964														
		3/4	2-1/2	UGMH12907	UGMG32903	UGMG34903	UGMG34904	UGMG34905														
		1	3	UGMH12S908*		UGMG34S965*	UGMG34S966*	UGMG34S967*														
		1-1/4	3	UGMH12S909*		UGMG34S968*	UGMG34S969*	UGMG34S970*														
		1-1/4	3	UGMH12S910*		UGMG34S968*	UGMG34S969*	UGMG34S970*														
5/16	5/16	7/16	2"	UGMH12020	UGMG32020	UGMG34971	UGMG34020	UGMG34972														
		13/16	2-1/2	UGMH12910	UGMG32904	UGMG34906	UGMG34907	UGMG34908														
		1	3	UGMH12S911*		UGMG34S973*	UGMG34S974*	UGMG34S975*														
3/8	3/8	1/2	2-1/2	UGMH12024	UGMG32024	UGMG34976	UGMG34024	UGMG34909	UGMG34977													
		1	3	UGMH12912	UGMG32905	UGMG34910	UGMG34911	UGMG34912	UGMG34978													
		1-1/4	3	UGMH12S913*		UGMG34S979*	UGMG34S980*	UGMG34S981*	UGMG34S982*													
		1-1/2	4	UGMH12S914*		UGMG34S983*	UGMG34S984*	UGMG34S985*	UGMG34S986*													
1/2	1/2	5/8	2-1/2	UGMH12032	UGMG32032	UGMG34032	UGMG34913	UGMG34914	UGMG34987	UGMG34988												
		1	3	UGMH12915	UGMG32906	UGMG34915	UGMG34916	UGMG34917	UGMG34918	UGMG34919												
		1-1/4	3-1/2	UGMH12916	UGMG32907	UGMG34920	UGMG34921	UGMG34922	UGMG34923	UGMG34924												
		1-5/8	4	UGMH12S917*		UGMG34S989*	UGMG34S990*	UGMG34S991*	UGMG34S992*	UGMG34S993*												
		2	4	UGMH12S918*		UGMG34S994*	UGMG34S995*	UGMG34S996*	UGMG34S997*	UGMG34S998*												

CHAMFER KEY
UGMG32

Mill Diameter (in.)	Chamfer Size
1/8	.004
3/16	.006
1/4	.007
5/16	.007
3/8	.011
1/2	.015
5/8	.015
3/4	.019
1	.019

Mill Dia. Tolerance (in)	Shank Dia. Tolerance
0 ~ -.0012	h5 * Shank Dia. ≥ Ø12 : h6

*Length of cut in excess of 3xD on 45° single-helix requires feed reduction of approximately 50%

NEXT PAGE ►


◎ : Excellent ○ : Good

ISO	P										M						K							
Material Description	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel		Stainless steel				Grey cast iron		Nodular cast iron		Malleable cast iron			
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20				
HRC	13	25	28	32	30	10	29	32	38	15	35	15	23	10	10	26	3	25		21				
HB	125	190	250	270	300	180	275	300	350	200	240	180	260	160	250	130	230							
Recommend	○	○	○	○	○	○	○	○	○	○	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎				
ISO	N										S						H							
Material Description	Aluminum-wrought alloy			Aluminum-cast, alloyed			Copper and Copper Alloys (Bronze / Brass)				Non Metallic Materials		Heat Resistant Super Alloys				Titanium Alloys		Hardened steel		Chilled Cast Iron		Hardened Cast Iron	
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41			
HRC											15	30	25	38	34			55	60	42	55			
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550			
Recommend											○	○	○	○	○	◎	◎	◎	◎	◎	◎			

HIGH PERFORMANCE SOLID CARBIDE END MILLS 5-FLUTE STANDARD LENGTH (PLAIN SHANK)

- Suitable for Titanium, Titanium Alloys, Inconel and Stainless Steels.
- Optimized flute design for chip evacuation and rigidity when machining difficult-to-cut materials.

- Special roughing profile for machining Titanium and Titanium Alloys.
- Longer tool life with special coating.



OD (D1)	SD (D2)	LOC (L1)	OAL (L2)	Square EDP No.	Chamfer EDP No.	Corner Radius									
						.015		.030		.060	.090	.125	.190	.250	
						EDP No.		EDP No.		EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
5/8	5/8	3/4	3	UGMH12040	UGMG32040		UGMG34040	UGMG34925	UGMG34999	UGMG34801					
		1-1/4	3-1/2	UGMH12919	UGMG32908	UGMG34926	UGMG34927	UGMG34928	UGMG34929	UGMG34930					
		1-5/8	4	UGMH12920			UGMG34802	UGMG34803	UGMG34804	UGMG34805					
		2-1/8	4-1/2	UGMH12S921*			UGMG34S806*	UGMG34S807*	UGMG34S808*	UGMG34S809*					
		2-1/2	5	UGMH12S922*			UGMG34S810*	UGMG34S811*	UGMG34S812*	UGMG34S813*					
3/4	3/4	1	3-1/2	UGMH12048	UGMG32048		UGMG34048	UGMG34931	UGMG34932	UGMG34814	UGMG34815	UGMG34816			
		1-1/2	4	UGMH12923	UGMG32909	UGMG34933	UGMG34934	UGMG34935	UGMG34936	UGMG34937	UGMG34938	UGMG34817			
		1-7/8	5	UGMH12924			UGMG34818	UGMG34819	UGMG34820	UGMG34821	UGMG34822	UGMG34823			
		2-1/4	5	UGMH12925			UGMG34824	UGMG34825	UGMG34826	UGMG34827	UGMG34828	UGMG34829			
		2-3/4	5	UGMH12S926*			UGMG34S830*	UGMG34S831*	UGMG34S832*	UGMG34S833*	UGMG34S834*	UGMG34S835*			
		3-1/4	6	UGMH12S927*			UGMG34S836*	UGMG34S837*	UGMG34S838*	UGMG34S839*	UGMG34S840*	UGMG34S841*			
1	1	1-1/8	4	UGMH12064	UGMG32064		UGMG34064	UGMG34939	UGMG34940	UGMG34842	UGMG34843	UGMG34844			
		1-1/2	4	UGMH12928	UGMG32910	UGMG34941	UGMG34942	UGMG34943	UGMG34944	UGMG34945	UGMG34946	UGMG34845			
		2	5	UGMH12929	UGMG32911		UGMG34947	UGMG34948	UGMG34949	UGMG34846	UGMG34847	UGMG34848			
		2-5/8	5	UGMH12930			UGMG34849	UGMG34850	UGMG34851	UGMG34852	UGMG34853	UGMG34854			
		3-1/4	6	UGMH12S931*			UGMG34S855*	UGMG34S856*	UGMG34S857*	UGMG34S858*	UGMG34S859*	UGMG34S860*			
		4-1/4	7	UGMH12S932*			UGMG34S861*	UGMG34S862*	UGMG34S863*	UGMG34S864*	UGMG34S865*	UGMG34S866*			
		1-1/4	4-1/2	UGMH12116			UGMG34116	UGMG34867	UGMG34868	UGMG34869	UGMG34870				
1-1/4	1-1/4	2	4-1/2	UGMH12933			UGMG34871	UGMG34872	UGMG34873	UGMG34874	UGMG34875				
		2-5/8	5-1/2	UGMH12934			UGMG34876	UGMG34877	UGMG34878	UGMG34879	UGMG34880				
		3-1/4	6	UGMH12935			UGMG34881	UGMG34882	UGMG34883	UGMG34884	UGMG34885				
		4-1/2	7	UGMH12S936*			UGMG34S886*	UGMG34S887*	UGMG34S888*	UGMG34S889*	UGMG34S890*				
							UGMG34S886*	UGMG34S887*	UGMG34S888*	UGMG34S889*	UGMG34S890*				

Mill Dia. Tolerance (in)	Shank Dia. Tolerance
0 ~ -.0012	h5 * Shank Dia. ≥ Ø12 : h6

*Length of cut in excess of 3xD on 45° single-helix requires feed reduction of approximately 50%


◎ : Excellent ○ : Good

ISO	P										M						K							
Material Description	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel		Stainless steel				Grey cast iron		Nodular cast iron		Malleable cast iron			
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20				
HRC	13	25	28	32	30	10	29	32	38	15	35	15	23	10	10	26	3	25		21				
HB	125	190	250	270	300	180	275	300	350	200	240	180	260	160	250	130	230							
Recommend	○	○	○	○	○	○	○	○	○	○	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎				
ISO	N										S						H							
Material Description	Aluminum-wrought alloy			Aluminum-cast, alloyed			Copper and Copper Alloys (Bronze / Brass)				Non Metallic Materials		Heat Resistant Super Alloys				Titanium Alloys		Hardened steel		Chilled Cast Iron		Hardened Cast Iron	
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41			
HRC											15	30												

HIGH PERFORMANCE SOLID CARBIDE END MILLS
5-FLUTE EXTENDED LENGTH (PLAIN SHANK)

SERIES
Square **UGMH06**
Corner Radius **UGMH07**

- Suitable for Titanium, Titanium Alloys, Inconel and Stainless Steels.
- Optimized flute design for chip evacuation and rigidity when machining difficult-to-cut materials.
- Special roughing profile for machining Titanium and Titanium Alloys.
- Longer tool life with special coating.



CARBIDE 5 43°/44°/45° PLAIN Y Coating p.22

Unit : INCH

OD (D1)	SD (D2)	LOC (L1)	LBS (L3)	OAL (L2)	Neck Dia (D3)	Square EDP No.	Corner Radius								
							.030 EDP No.	.060 EDP No.	.090 EDP No.	.125 EDP No.	.190 EDP No.	.250 EDP No.			
1/8	1/8	5/32	3/8	3	.113	UGMH06008	UGMH07008								
		5/32	1/2	3	.113	UGMH06901	UGMH07901								
		5/32	5/8	3	.113	UGMH06902	UGMH07902								
3/16	3/16	7/32	1/2	3	.176	UGMH06012	UGMH07012								
		7/32	3/4	3	.176	UGMH06903	UGMH07903								
		7/32	1	3	.176	UGMH06904	UGMH07904								
1/4	1/4	3/8	3/4	4	.230	UGMH06016	UGMH07016	UGMH07905							
		3/8	1-1/8	4	.230	UGMH06905	UGMH07906	UGMH07907							
		3/8	2-1/8	4	.230	UGMH06906	UGMH07908	UGMH07909							
3/8	3/8	1/2	1-1/8	4	.344	UGMH06024	UGMH07024	UGMH07910	UGMH07911						
		1/2	2-1/8	4	.344	UGMH06907	UGMH07912	UGMH07913	UGMH07914						
		1/2	3-1/8	5	.344	UGMH06923	UGMH07804	UGMH07805	UGMH07806						
		1/2	3-1/8	6	.344	UGMH06908	UGMH07915	UGMH07916	UGMH07917						
1/2	1/2	5/8	1-1/2	4	.461	UGMH06032	UGMH07032	UGMH07921	UGMH07922	UGMH07923					
		5/8	2-1/4	4	.461	UGMH06910	UGMH07924	UGMH07925	UGMH07926	UGMH07927					
		5/8	3-3/8	5	.461	UGMH06924	UGMH07807	UGMH07808	UGMH07809	UGMH07810					
		5/8	3-3/8	6	.461	UGMH06911	UGMH07928	UGMH07929	UGMH07930	UGMH07931					
5/8	5/8	3/4	1-5/8	4	.586	UGMH06040	UGMH07040	UGMH07936	UGMH07937	UGMH07938					
		3/4	2-3/8	6	.586	UGMH06913	UGMH07939	UGMH07940	UGMH07941	UGMH07942					
		3/4	3-3/8	6	.586	UGMH06914	UGMH07943	UGMH07944	UGMH07945	UGMH07946					
		3/4	4-1/8	6	.586	UGMH06915	UGMH07947	UGMH07948	UGMH07949	UGMH07950					

Mill Dia. Tolerance (in) 0 ~ - .0012 Shank Dia. Tolerance h5 * Shank Dia. ≥ Ø1/2 : h6 Feed to be reduced by approximately 50% if L.O.C. (Length Of Cut) is over 3x D NEXT PAGE ▶

ISO Material Description

Material Description	P										M				K					
	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel		Stainless steel		Grey cast iron		Nodular cast iron		Malleable cast iron	
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20
HRc	13	25	28	32	30	10	29	32	38	15	35	15	23	10	10	26	3	25		
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250	130	230
Recommend	○	○	○	○	○	○	○	○	○	○	○	◎	◎	◎	○	○	○	○	○	○


Material Description	N				S								H								
	Aluminum-wrought alloy		Aluminum-cast, alloyed		Copper and Copper Alloys (Bronze / Brass)		Non Metallic Materials		Heat Resistant Super Alloys				Titanium Alloys		Hardened steel	Chilled Cast Iron	Hardened Cast Iron				
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41
HRc											15	30	25	38	34			55	60	42	55
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550
Recommend											○	○	○	○	○	◎	◎				

◎ : Excellent ○ : Good

HIGH PERFORMANCE SOLID CARBIDE END MILLS
5-FLUTE EXTENDED LENGTH (PLAIN SHANK)

SERIES
Square **UGMH06**
Corner Radius **UGMH07**

- Suitable for Titanium, Titanium Alloys, Inconel and Stainless Steels.
- Optimized flute design for chip evacuation and rigidity when machining difficult-to-cut materials.
- Special roughing profile for machining Titanium and Titanium Alloys.
- Longer tool life with special coating.



CARBIDE 5 43°/44°/45° PLAIN Y Coating p.22

Unit : INCH

OD (D1)	SD (D2)	LOC (L1)	LBS (L3)	OAL (L2)	Neck Dia (D3)	Square EDP No.	Corner Radius							
							.030 EDP No.	.060 EDP No.	.090 EDP No.	.125 EDP No.	.190 EDP No.	.250 EDP No.		
3/4	3/4	1-1/8	2	4	.711	UGMH06048	UGMH07048	UGMH07951	UGMH07952	UGMH07953	UGMH07954	UGMH07955		
		1-1/8	2-5/8	5	.711	UGMH06916	UGMH07956	UGMH07957	UGMH07958	UGMH07959	UGMH07960	UGMH07961		
		1-1/8	3-1/4	6	.711	UGMH06917	UGMH07962	UGMH07963	UGMH07964	UGMH07965	UGMH07966	UGMH07967		
1	1	1-1/8	4-1/4	7	.711	UGMH06918	UGMH07968	UGMH07969	UGMH07970	UGMH07971	UGMH07972	UGMH07973		
		1-1/4	2-1/4	4	.961	UGMH06064	UGMH07064	UGMH07974	UGMH07975	UGMH07976	UGMH07977	UGMH07978		
		1-1/4	2-5/8	5	.961	UGMH06919	UGMH07979	UGMH07980	UGMH07981	UGMH07982	UGMH07983	UGMH07984		
		1-1/4	3-1/4	6	.961	UGMH06920	UGMH07985	UGMH07986	UGMH07987	UGMH07988	UGMH07989	UGMH07990		
1	1	1-1/4	4-1/4	7	.961	UGMH06921	UGMH07991	UGMH07992	UGMH07993	UGMH07994	UGMH07995	UGMH07996		
		1-1/4	5-1/4	8	.961	UGMH06922	UGMH07997	UGMH07998	UGMH07999	UGMH07801	UGMH07802	UGMH07803		

Mill Dia. Tolerance (in) 0 ~ - .0012 Shank Dia. Tolerance h5 * Shank Dia. ≥ Ø1/2 : h6 Feed to be reduced by approximately 50% if L.O.C. (Length Of Cut) is over 3x D

ISO Material Description

Material Description	P										M				K					
	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel		Stainless steel		Grey cast iron		Nodular cast iron		Malleable cast iron	
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20
HRc	13	25	28	32	30	10	29	32	38	15	35	15	23	10	10	26	3	25		
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250	130	230
Recommend	○	○	○	○	○	○	○	○	○	○	○	◎	◎	◎	○	○	○	○	○	○

Material Description	N				S								H								
	Aluminum-wrought alloy		Aluminum-cast, alloyed		Copper and Copper Alloys (Bronze / Brass)		Non Metallic Materials		Heat Resistant Super Alloys				Titanium Alloys		Hardened steel	Chilled Cast Iron	Hardened Cast Iron				
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41
HRc											15	30	25	38	34			55	60	42	55
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550
Recommend											○	○	○	○	○	◎	◎				


◎ : Excellent ○ : Good

HIGH PERFORMANCE SOLID CARBIDE END MILLS - TitaNox Power HPC
5-FLUTE STANDARD LENGTH (PLAIN SHANK)

SERIES
 Square **EMI42**
 Corner Radius **EMI43**

► New design enhances chip space in heavy cuts, while still maintaining rigidity in peel milling.
 ► Unequal index design for Chatter-Free cutting

► high performance milling of Stainless Steel, Titanium, and Heat-Resistant Super Alloys



Unit: INCH

OD (D1)	SD (D2)	LOC (L1)	OAL (L2)	Square EDP No.	Corner Radius							
					.015 EDP No.	.030 EDP No.	.060 EDP No.	.090 EDP No.	.125 EDP No.	.190 EDP No.	.250 EDP No.	
1/4	1/4	3/8	2	EMI42016	EMI43016	EMI43901	EMI43902					
		1/2	2_1/2	EMI42901	EMI43903	EMI43904	EMI43905					
		3/4	2_1/2	EMI42902	EMI43906	EMI43907	EMI43908					
5/16	5/16	7/16	2	EMI42020	EMI43020	EMI43909						
		13/16	2_1/2	EMI42903	EMI43910	EMI43911						
3/8	3/8	1/2	2_1/2	EMI42024	EMI43024	EMI43912	EMI43913	EMI43914				
		1	3	EMI42904	EMI43915	EMI43916	EMI43917	EMI43918				
1/2	1/2	1_1/4	3	EMI42905	EMI43919	EMI43920	EMI43921	EMI43922				
		5/8	2_1/2	EMI42032	EMI43032	EMI43923	EMI43924	EMI43925	EMI43926			
		1	3	EMI42906	EMI43927	EMI43928	EMI43929	EMI43930	EMI43931			
		1_1/4	3	EMI42907	EMI43932	EMI43933	EMI43934	EMI43935	EMI43936			
5/8	5/8	1_5/8	4	EMI42908	EMI43937	EMI43938	EMI43939	EMI43940	EMI43941			
		3/4	3	EMI42040		EMI43040	EMI43942	EMI43943	EMI43944			
		1_1/4	3_1/2	EMI42909	EMI43945	EMI43946	EMI43947	EMI43948	EMI43949			
3/4	3/4	1_5/8	4	EMI42910		EMI43950	EMI43951	EMI43952	EMI43953			
		2_1/8	4_1/2	EMI42911		EMI43954	EMI43955	EMI43956	EMI43957			
		1	3_1/2	EMI42048		EMI43048	EMI43958	EMI43959	EMI43960	EMI43961		
		1_1/2	4	EMI42912	EMI43962	EMI43963	EMI43964	EMI43965	EMI43966	EMI43967	EMI43968	
3/4	3/4	1_5/8	5	EMI42913		EMI43969		EMI43970	EMI43973	EMI43971	EMI43972	
		2_1/4	5	EMI42914	EMI43974	EMI43975	EMI43976	EMI43977	EMI43978	EMI43979	EMI43980	

Mill Dia. Tolerance (in)	Shank Dia. Tolerance
0 ~ - .0012	h5 * Shank Dia. ≥ Ø1/2 : h6

Feed to be reduced by approximately 50% if L.O.C. (Length Of Cut) is over 3xD
 • TitaNox Power HPC Square Tools are designed with a true sharp corner while TitaNox Power Square tools feature a dubbed corner for extra protection

NEXT PAGE ►

◎: Excellent ○: Good

ISO Material Description	P										M				K					
	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel		Stainless steel		Grey cast iron		Nodular cast iron		Malleable cast iron	
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20
HRc	13	25	28	32	30	10	29	32	38	15	35	15	23	10	10	26	3	25	10	21
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250	130	230
Recommend	○	○	○	○	○	○	○	○	○	○	◎	◎	◎	◎	○	○	○	○	○	○


ISO Material Description	N					S										H					
	Aluminum-wrought alloy		Aluminum-cast, alloyed		Copper and Copper Alloys (Bronze / Brass)	Non Metallic Materials		Heat Resistant Super Alloys					Titanium Alloys		Hardened steel	Chilled Cast Iron	Hardened Cast Iron				
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41
HRc											15	30	25	38	34			55	60	42	55
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550
Recommend											○	○	○	○	○	◎	◎				

HIGH PERFORMANCE SOLID CARBIDE END MILLS - TitaNox Power HPC
5-FLUTE STANDARD LENGTH (PLAIN SHANK)

SERIES
 Square **EMI42**
 Corner Radius **EMI43**

► New design enhances chip space in heavy cuts, while still maintaining rigidity in peel milling.
 ► Unequal index design for Chatter-Free cutting

► high performance milling of Stainless Steel, Titanium, and Heat-Resistant Super Alloys




Unit: INCH


OD (D1)	SD (D2)	LOC (L1)	OAL (L2)	Square EDP No.	Corner Radius						
					.015 EDP No.	.030 EDP No.	.060 EDP No.	.090 EDP No.	.125 EDP No.	.190 EDP No.	.250 EDP No.
1	1	1_1/8	4	EMI42064			EMI43064		EMI43981		
		1_1/2	4	EMI42915	EMI43982	EMI43983	EMI43984		EMI43985		
		2	5	EMI42916	EMI43986	EMI43987	EMI43988	EMI43989	EMI43990		EMI43991
		2_5/8	5	EMI42917		EMI43992	EMI43993		EMI43994		EMI43995
		3_1/4	6	EMI42918		EMI43996	EMI43997	EMI43998	EMI43999		EMI43801

Mill Dia. Tolerance (in)	Shank Dia. Tolerance
0 ~ - .0012	h5 * Shank Dia. ≥ Ø1/2 : h6

Feed to be reduced by approximately 50% if L.O.C. (Length Of Cut) is over 3xD
 • TitaNox Power HPC Square Tools are designed with a true sharp corner while TitaNox Power Square tools feature a dubbed corner for extra protection



Unequal Index
 Exclusively Designed Unique Geometry applied to Reduce Vibration and also to achieve Excellent surface finish



Core Design
 YG-1's High Performance Core Geometries is designed for superior chip evacuation. It's excellent at Slotting & Heavy Profiling.

◎: Excellent ○: Good


ISO Material Description	P										M				K					
	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel		Stainless steel		Grey cast iron		Nodular cast iron		Malleable cast iron	
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20
HRc	13	25	28	32	30	10	29	32	38	15	35	15	23	10	10	26	3	25	10	21
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250	130	230
Recommend	○	○	○	○	○	○	○	○	○	○	◎	◎	◎	◎	○	○	○	○	○	○

ISO Material Description	N					S										H					
	Aluminum-wrought alloy		Aluminum-cast, alloyed		Copper and Copper Alloys (Bronze / Brass)	Non Metallic Materials		Heat Resistant Super Alloys					Titanium Alloys		Hardened steel	Chilled Cast Iron	Hardened Cast Iron				
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41
HRc											15	30	25	38	34			55	60	42	55
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550
Recommend											○	○	○	○	○	◎	◎				

**HIGH PERFORMANCE SOLID CARBIDE END MILLS
4-FLUTE DOUBLE CORE EXTENDED LENGTH PLAIN SHANK)**

Corner Radius **GMG40** SERIES

- ▶ Double core end mill has a unique flute design for excellent chip evacuation and higher rigidity.
- ▶ The double core adds stability and aids chip flow, reducing tool deflection, improving dimensional stability and workpiece accuracy.



Unit : METRIC

Metric	Inch	OD (D1)	SD (D2)	LOC (L1)	LBS (L3)	OAL (L2)	Neck Dia (D3)	Corner Radius								
								0.50 EDP No.	1.00 EDP No.	1.50 EDP No.	2.00 EDP No.	3.00 EDP No.	3.50 EDP No.	4.00 EDP No.		
6	.2362	6	13	20	57	5.5		GMG40060	GMG40901							
8	.315	8	19	25	63	7.5		GMG40080	GMG40902	GMG40903	GMG40904					
10	.3937	10	22	30	72	9.2		GMG40100	GMG40905	GMG40906	GMG40907					
12	.4724	12	26	35	83	11.0		GMG40120	GMG40908	GMG40909	GMG40910	GMG40911				
14	.5512	14	26	35	83	13.0			GMG40140		GMG40912					
16	.6299	16	35	43	92	15.0			GMG40160	GMG40913	GMG40914	GMG40915			GMG40916	
20	.7874	20	44	56	110	19.0			GMG40200	GMG40917	GMG40918	GMG40919	GMG40920		GMG40921	
25	.9843	25	55	70	130	24.0			GMG40250	GMG40922	GMG40923	GMG40924			GMG40925	

Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
0 ~ - 0.03	h5 * Shank Dia. ≥ Ø12 : h6

© : Excellent ○ : Good


ISO Material Description	P										M				K					
	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel		Stainless steel		Grey cast iron		Nodular cast iron		Malleable cast iron	
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20
HRc	13	25	28	32	30	10	29	32	38	15	35	15	23	10	10	26	3	25		21
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250	130	230
Recommend	○	○	○	○	○	○	○	○	○	○	○	◎	◎	◎	○	○	○	○	○	○

ISO Material Description	N				S										H							
	Aluminum-wrought alloy		Aluminum-cast, alloyed		Copper and Copper Alloys (Bronze / Brass)		Non Metallic Materials		Heat Resistant Super Alloys					Titanium Alloys		Hardened steel	Chilled Cast Iron	Hardened Cast Iron				
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41	
HRc						15	30	25	38	34	15	30	25	38	34	400 Rm	1050 Rm	55	60	42	55	
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550	
Recommend						○	○	○	○	○	○	○	○	○	○	◎	◎					

**HIGH PERFORMANCE SOLID CARBIDE END MILLS
5-FLUTE EXTENDED LENGTH (PLAIN SHANK)**

Chamfer **GMG24, GMG26**
Corner Radius **GMG28, GMG30** SERIES

- ▶ Suitable for Titanium, Titanium Alloys, Inconel and Stainless Steels.
- ▶ Optimized flute design for chip evacuation and rigidity when machining difficult-to-cut materials.
- ▶ Special roughing profile for machining Titanium and Titanium Alloys.
- ▶ Longer tool life with special coating.



Unit : METRIC

Metric	Inch	OD (D1)	SD (D2)	LOC (L1)	OAL (L2)	Chamfer EDP No.	Corner Radius															
							0.30 EDP No.	0.50 EDP No.	1.00 EDP No.	1.50 EDP No.	2.00 EDP No.	2.50 EDP No.	3.00 EDP No.	4.00 EDP No.	5.00 EDP No.							
6	.2362	6	10	54	GMG24060																	
		6	13	57	GMG26060	GMG30060	GMG30901	GMG30902														
8	.315	8	12	58	GMG24080		GMG28080															
		8	19	63	GMG26080		GMG30080	GMG30903	GMG30904	GMG30905												
10	.3937	10	14	66	GMG24100		GMG28100															
		10	22	72	GMG26100		GMG30100	GMG30906	GMG30907	GMG30908												
12	.4724	12	16	73	GMG24120		GMG28120															
		12	26	83	GMG26120		GMG30120	GMG30909	GMG30910	GMG30911	GMG30912	GMG30913										
16	.6299	16	22	82	GMG24160			GMG28160														
		16	36	92	GMG26160			GMG30160	GMG30914	GMG30915	GMG30916	GMG30917	GMG30918									
20	.7874	20	26	92	GMG24200			GMG28200														
		20	44	104	GMG26200			GMG30200	GMG30919	GMG30920	GMG30921	GMG30922	GMG30923	GMG30924								
25	.9843	25	29	100	GMG24250			GMG28250														
		25	54	121	GMG26250				GMG30250	GMG30925	GMG30926	GMG30927	GMG30928	GMG30929	GMG30930							

Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
0 ~ - 0.03	h5 * Shank Dia. ≥ Ø12 : h6

CHAMFER KEY GMG24 | GMG26

Metric	Mill Diameter		Chamfer Size (mm)
	Metric	Inch	
6	.2362		0.20
8	.315		0.20
10	.3937		0.30
12	.4724		0.35
16	.6299		0.40
20	.7478		0.50
25	.9843		0.50

© : Excellent ○ : Good


ISO Material Description	P										M				K					
	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel		Stainless steel		Grey cast iron		Nodular cast iron		Malleable cast iron	
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20
HRc	13	25	28	32	30	10	29	32	38	15	35	15	23	10	10	26	3	25		21
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250	130	230
Recommend	○	○	○	○	○	○	○	○	○	○	○	◎	◎	◎	○	○	○	○	○	○

ISO Material Description	N				S										H							
	Aluminum-wrought alloy		Aluminum-cast, alloyed		Copper and Copper Alloys (Bronze / Brass)		Non Metallic Materials		Heat Resistant Super Alloys					Titanium Alloys		Hardened steel	Chilled Cast Iron	Hardened Cast Iron				
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41	
HRc						15	30	25	38	34	15	30	25	38	34	400 Rm	1050 Rm	55	60	42	55	
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550	
Recommend						○	○	○	○	○	○	○	○	○	○	◎	◎					

RECOMMENDED CUTTING CONDITIONS – INCH


UGMG42, UGMG43 SERIES

4 FLUTES DOUBLE CORE - Side cutting



RPM = rev./min. Feed = in./min.
Vc = ft./min. fz = in./tooth

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)						
						1/4	5/16	3/8	1/2	5/8	3/4	1
P	1-5	Non-alloy steel	0.4D	1.0D (0.7D)*	SFM (Vc)	525	525	525	525	525	525	525
					IPT (fz)	.0011	.0014	.0017	.0021	.0025	.0030	.0033
	RPM	8020	6420	5350	4010	3210	2670	2010				
	IPM (FEED)	35	36	36	34	32	32	27				
	6-8	Low alloy steel	0.4D	1.0D (0.7D)*	SFM (Vc)	525	525	525	525	525	525	525
					IPT (fz)	.0011	.0014	.0017	.0021	.0025	.0030	.0033
	RPM	8020	6420	5350	4010	3210	2670	2010				
	IPM (FEED)	35	36	36	34	32	32	27				
	9	Low alloy steel	0.4D	1.0D (0.7D)*	SFM (Vc)	490	490	490	490	490	490	490
					IPT (fz)	.0010	.0014	.0017	.0019	.0025	.0028	.0033
RPM	7490	5990	4990	3740	2990	2500	1870					
IPM (FEED)	30	34	34	28	30	28	25					
10	High alloyed steel, and tool steel	0.4D	1.0D (0.7D)*	SFM (Vc)	490	490	490	490	490	490	490	
				IPT (fz)	.0011	.0014	.0018	.0021	.0026	.0030	.0033	
RPM	7490	5990	4990	3740	2990	2500	1870					
IPM (FEED)	33	34	36	31	31	30	25					
11.1	High alloyed steel, and tool steel	0.4D	1.0D (0.7D)*	SFM (Vc)	490	490	490	490	490	490	490	
				IPT (fz)	.0010	.0014	.0017	.0019	.0025	.0028	.0033	
RPM	7490	5990	4990	3740	2990	2500	1870					
IPM (FEED)	30	34	34	28	30	28	25					
M	12-13	Stainless steel (SUS 420, X40Cr13, 420)	0.4D	1.0D (0.7D)	SFM (Vc)	510	510	510	510	510	510	
					IPT (fz)	.0013	.0018	.0022	.0026	.0034	.0037	.0045
	RPM	7790	6230	5190	3900	3120	2600	1950				
	IPM (FEED)	41	45	46	41	42	38	35				
	14.1	Stainless steel (SUS 316, 316, X5CrNiMo 17 12 2)	0.4D	1.0D (0.7D)*	SFM (Vc)	345	345	345	345	345	345	345
					IPT (fz)	.0010	.0013	.0016	.0019	.0024	.0028	.0032
RPM	5270	4220	3510	2640	2110	1760	1320					
IPM (FEED)	21	22	22	20	20	20	17					
14.2	Stainless steel (SUS 630, PH 15-5)	0.4D	0.6D	SFM (Vc)	145	145	145	145	145	145	145	
				IPT (fz)	.0006	.0008	.0010	.0013	.0016	.0018	.0021	
RPM	2220	1770	1480	1110	890	740	550					
IPM (FEED)	5	6	6	6	6	5	5					
K	15-20	Grey cast iron	0.4D	1.0D (0.7D)*	SFM (Vc)	575	575	575	575	575	575	575
					IPT (fz)	.0008	.0011	.0014	.0017	.0021	.0024	.0028
					RPM	8790	7030	5860	4390	3510	2930	2200
					IPM (FEED)	28	31	33	30	29	28	25
S	31-35	Heat Resistant Super Alloys (X12 NiCrSi 36-16, 1.4864, Inconel 718, NiCr20TiAl, 2.4631, NiCu30Al, 2.4375, G-X120Mn12, 1.3401)	0.3D	0.6D	SFM (Vc)	105	105	105	105	105	105	105
					IPT (fz)	.0008	.0010	.0013	.0015	.0019	.0022	.0026
					RPM	1600	1280	1070	800	640	530	400
	IPM (FEED)	5	5	6	5	5	5	4				
	36-37	Titanium Alloys (HB 400 Rm, HB 1050 Rm TiAl6V4, 3.7165)	0.4D	1.0D (0.7D)*	SFM (Vc)	230	230	230	230	230	230	230
					IPT (fz)	.0013	.0019	.0022	.0026	.0034	.0037	.0045
RPM					3510	2810	2340	1760	1410	1170	880	
IPM (FEED)	18	21	21	18	19	17	16					



NOTES:

- ▶ Maximum recommended depth shown
- ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
- ▶ Feed to be reduced by approximately 50% if L.O.C. (length of cut) is over 3xD
- ▶ Reduce speed and feed recommendations for materials harder than listed
- ▶ Recommendations above are based on ideal conditions.


Adjust parameters accordingly for smaller taper machining centers or less rigid conditions

* (0.7D): UGMG42K998, UGMG42K999, UGMGK801
0.7D cutting depth for slotting and side cutting applications due to short double-core length

RECOMMENDED CUTTING CONDITIONS – INCH


UGMG42, UGMG43 SERIES

4 FLUTES DOUBLE CORE - Slotting



RPM = rev./min. Feed = in./min.
Vc = ft./min. fz = in./tooth

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)						
						1/4	5/16	3/8	1/2	5/8	3/4	1
P	1-5	Non-alloy steel	1.0D	1.0D (0.7D)*	SFM (Vc)	410	410	410	410	410	410	410
					IPT (fz)	.0010	.0013	.0017	.0019	.0025	.0028	.0033
	RPM	6260	5010	4180	3130	2510	2090	1570				
	IPM (FEED)	25	26	28	24	25	23	21				
	6-8	Low alloy steel	1.0D	1.0D (0.7D)*	SFM (Vc)	410	410	410	410	410	410	410
					IPT (fz)	.0010	.0013	.0017	.0019	.0025	.0028	.0033
	RPM	6260	5010	4180	3130	2510	2090	1570				
	IPM (FEED)	25	26	28	24	25	23	21				
	9	Low alloy steel	1.0D	1.0D (0.7D)*	SFM (Vc)	395	395	395	395	395	395	395
					IPT (fz)	.0010	.0013	.0017	.0019	.0025	.0028	.0030
RPM	6040	4830	4020	3020	2410	2010	1510					
IPM (FEED)	24	25	27	23	24	23	18					
10	High alloyed steel, and tool steel	1.0D	1.0D (0.7D)*	SFM (Vc)	410	410	410	410	410	410	410	
				IPT (fz)	.0010	.0013	.0017	.0019	.0025	.0028	.0033	
RPM	6260	5010	4180	3130	2510	2090	1570					
IPM (FEED)	25	26	28	24	25	23	21					
11.1	High alloyed steel, and tool steel	1.0D	1.0D (0.7D)*	SFM (Vc)	395	395	395	395	395	395	395	
				IPT (fz)	.0010	.0013	.0017	.0019	.0025	.0028	.0030	
RPM	6040	4830	4020	3020	2410	2010	1510					
IPM (FEED)	24	25	27	23	24	23	18					
M	12-13	Stainless steel (SUS 420, X40Cr13, 420)	1.0D	1.0D (0.7D)	SFM (Vc)	410	410	410	410	410	410	410
					IPT (fz)	.0013	.0018	.0022	.0026	.0032	.0037	.0041
	RPM	6260	5010	4180	3130	2510	2090	1570				
	IPM (FEED)	33	36	37	33	32	31	26				
	14.1	Stainless steel (SUS 316, 316, X5CrNiMo 17 12 2)	1.0D	1.0D (0.7D)*	SFM (Vc)	280	280	280	280	280	280	280
					IPT (fz)	.0010	.0013	.0016	.0019	.0024	.0028	.0032
RPM	4280	3420	2850	2140	1710	1430	1070					
IPM (FEED)	17	18	18	16	16	16	14					
14.2	Stainless steel (SUS 630, PH 15-5)	1.0D	0.5D	SFM (Vc)	120	120	120	120	120	120	120	
				IPT (fz)	.0006	.0008	.0010	.0013	.0016	.0018	.0021	
RPM	1830	1470	1220	920	730	610	460					
IPM (FEED)	4	5	5	5	5	4	4					
K	15-20	Grey cast iron	1.0D	1.0D (0.7D)*	SFM (Vc)	460	460	460	460	460	460	460
					IPT (fz)	.0008	.0011	.0014	.0017	.0021	.0024	.0026
					RPM	7030	5620	4690	3510	2810	2340	1760
					IPM (FEED)	22	25	26	24	24	22	18
S	31-35	Heat Resistant Super Alloys (X12 NiCrSi 36-16, 1.4864, Inconel 718, NiCr20TiAl, 2.4631, NiCu30Al, 2.4375, G-X120Mn12, 1.3401)	1.0D	0.4D	SFM (Vc)	80	80	80	80	80	80	80
					IPT (fz)	.0007	.0009	.0012	.0014	.0017	.0020	.0022
					RPM	1220	980	810	610	490	410	310
	IPM (FEED)	3	4	4	3	3	3	3				
	36-37	Titanium Alloys (HB 400 Rm, HB 1050 Rm TiAl6V4, 3.7165)	1.0D	1.0D (0.7D)*	SFM (Vc)	180	180	180	180	180	180	180
					IPT (fz)	.0013	.0018	.0022	.0026	.0034	.0037	.0041
RPM					2750	2200	1830	1380	1100	920	690	
IPM (FEED)	14	16	16	14	15	14	11					



NOTES:

- ▶ Maximum recommended depth shown
- ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
- ▶ Feed to be reduced by approximately 50% if L.O.C. (length of cut) is over 3xD
- ▶ Reduce speed and feed recommendations for materials harder than listed
- ▶ Recommendations above are based on ideal conditions.


Adjust parameters accordingly for smaller taper machining centers or less rigid conditions

* (0.7D): UGMG42K998, UGMG42K999, UGMGK801
0.7D cutting depth for slotting and side cutting applications due to short double-core length

RECOMMENDED CUTTING CONDITIONS – INCH


UGMH12, UGMG32, UE5G32 UGMG34, UGMH06, UGMH07 SERIES

5 FLUTES - Side cutting



RPM = rev./min. Feed = in./min.
Vc = ft./min. fz = in./tooth

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)													
						1/8	3/16	1/4	5/16	3/8	1/2	9/16	5/8	11/16	3/4	1	1 1/4		
P	1-5	Non-alloy steel	0.3D	1.5D	SFM (Vc)	470	470	470	470	470	470	470	470	470	470	470	470	470	470
					IPT (fz)	.0004	.0007	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040	.0046		
					RPM	14360	9570	7180	5740	4790	3590	3190	2870	2610	2390	1800	1440		
	6-8	Low alloy steel	0.3D	1.5D	SFM (Vc)	470	470	470	470	470	470	470	470	470	470	470	470	470	
					IPT (fz)	.0004	.0007	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040	.0046		
					RPM	14360	9570	7180	5740	4790	3590	3190	2870	2610	2390	1800	1440		
	9	High alloyed steel, and tool steel	0.3D	1.5D	SFM (Vc)	330	330	330	330	330	330	330	330	330	330	330	330	330	
					IPT (fz)	.0004	.0007	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040	.0046		
					RPM	10080	6720	5040	4030	3360	2520	2240	2020	1830	1680	1260	1010		
	10	High alloyed steel, and tool steel	0.3D	1.5D	SFM (Vc)	470	470	470	470	470	470	470	470	470	470	470	470	470	
					IPT (fz)	.0004	.0007	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040	.0046		
					RPM	14360	9570	7180	5740	4790	3590	3190	2870	2610	2390	1800	1440		
	11.1	High alloyed steel, and tool steel	0.3D	1.5D	SFM (Vc)	330	330	330	330	330	330	330	330	330	330	330	330	330	
					IPT (fz)	.0004	.0007	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040	.0046		
					RPM	10080	6720	5040	4030	3360	2520	2240	2020	1830	1680	1260	1010		
	M	12-13	Stainless steel (SUS 420, X40Cr13, 420)	0.3D	1.5D	SFM (Vc)	385	385	385	385	385	385	385	385	385	385	385	385	
						IPT (fz)	.0003	.0004	.0009	.0010	.0012	.0018	.0020	.0021	.0022	.0024	.0028	.0033	
						RPM	11760	7840	5880	4710	3920	2940	2610	2350	2140	1960	1470	1180	
		14.1	Stainless steel (SUS 316, 316, XSGNiMo 17 122)	0.3D	1.5D	SFM (Vc)	270	270	270	270	270	270	270	270	270	270	270	270	
						IPT (fz)	.0004	.0005	.0012	.0013	.0015	.0025	.0026	.0027	.0028	.0030	.0035	.0041	
RPM						8250	5500	4130	3300	2750	2060	1830	1650	1500	1380	1030	830		
14.2		Stainless steel (SUS 630, PH 15-5)	0.3D	1.5D	SFM (Vc)	195	195	195	195	195	195	195	195	195	195	195	195		
					IPT (fz)	.0004	.0005	.0012	.0013	.0015	.0025	.0026	.0027	.0028	.0030	.0035	.0041		
					RPM	5960	3970	2980	2380	1990	1490	1320	1190	1080	990	740	600		
K		15-20	Grey cast iron	0.3D	1.5D	SFM (Vc)	350	350	350	350	350	350	350	350	350	350	350	350	
						IPT (fz)	.0006	.0008	.0017	.0019	.0025	.0031	.0034	.0038	.0041	.0044	.0050	.0057	
						RPM	10700	7130	5350	4280	3570	2670	2380	2140	1940	1780	1340	1070	
		S	31-35	Heat Resistant Super Alloys (X12 NiCrSi 36-16, 1.4864, Inconel 718, NiCr20TiAl, 2.4631, NiCu30Al, 2.4375, G-X120Mn12, 1.3401)	0.1D	1.5D	SFM (Vc)	100	100	100	100	100	100	100	100	100	100	100	100
							IPT (fz)	.0004	.0005	.0008	.0009	.0011	.0017	.0018	.0019	.0019	.0021	.0024	.0027
							RPM	3060	2040	1530	1220	1020	760	680	610	560	510	380	310
			36-37	Titanium Alloys (HB 400 Rm, HB 1050 Rm TiAl6V4, 3.7165)	0.2D	1.5D	SFM (Vc)	225	225	225	225	225	225	225	225	225	225	225	225
							IPT (fz)	.0004	.0004	.0011	.0011	.0013	.0022	.0023	.0024	.0025	.0027	.0031	.0036
							RPM	6880	4580	3440	2750	2290	1720	1530	1380	1250	1150	860	690




- NOTES:**
- ▶ Maximum recommended depth shown
 - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
 - ▶ Feed to be reduced by approximately 50% if L.O.C. (length of cut) is over 3xD
 - ▶ Reduce speed and feed recommendations for materials harder than listed
 - ▶ Recommendations above are based on ideal conditions.
- Adjust parameters accordingly for smaller taper machining centers or less rigid conditions

RECOMMENDED CUTTING CONDITIONS – INCH


EMI42, EMI43 SERIES

5 FLUTES (TitaNox Power HPC) - Heavy Side cutting



RPM = rev./min. Feed = in./min.
Vc = ft./min. fz = in./tooth

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)											
						3/16	1/4	5/16	3/8	1/2	5/8	3/4	1				
P	1-5	Non-alloy steel	0.5D	1.5D	SFM (Vc)	500	500	500	500	500	500	500	500	500	500	500	
					IPT (fz)	.0013	.0016	.0018	.0022	.0031	.0037	.0043	.0049				
					RPM	10190	7640	6110	5090	3820	3060	2550	1910				
	6-8	Low alloy steel	0.5D	1.5D	SFM (Vc)	500	500	500	500	500	500	500	500	500	500		
					IPT (fz)	.0013	.0016	.0018	.0022	.0031	.0037	.0043	.0049				
					RPM	10190	7640	6110	5090	3820	3060	2550	1910				
	9	High alloyed steel, and tool steel	0.5D	1.5D	SFM (Vc)	400	400	400	400	400	400	400	400	400	400		
					IPT (fz)	.0008	.0012	.0014	.0017	.0024	.0028	.0033	.0038				
					RPM	8150	6110	4890	4070	3060	2440	2040	1530				
	10	High alloyed steel, and tool steel	0.5D	1.5D	SFM (Vc)	450	450	450	450	450	450	450	450	450	450		
					IPT (fz)	.0013	.0016	.0018	.0022	.0031	.0037	.0043	.0049				
					RPM	9170	6880	5500	4580	3440	2750	2290	1720				
	11.1	High alloyed steel, and tool steel	0.5D	1.5D	SFM (Vc)	400	400	400	400	400	400	400	400	400			
					IPT (fz)	.0008	.0012	.0014	.0017	.0024	.0028	.0033	.0038				
					RPM	8150	6110	4890	4070	3060	2440	2040	1530				
	M	12-13	Stainless steel (SUS 420, X40Cr13, 420)	0.5D	1.5D	SFM (Vc)	250	250	250	250	250	250	250	250	250	250	
						IPT (fz)	.0007	.0010	.0012	.0015	.0021	.0024	.0028	.0032			
						RPM	5090	3820	3060	2550	1910	1530	1270	950			
		14.1	Stainless steel (SUS 316, 316, XSGNiMo 17 122)	0.5D	1.5D	SFM (Vc)	300	300	300	300	300	300	300	300	300		
						IPT (fz)	.0008	.0013	.0014	.0018	.0026	.0028	.0031	.0036			
						RPM	6110	4580	3670	3060	2290	1830	1530	1150			
		14.2	Stainless steel (SUS 630, PH 15-5)	0.5D	1.5D	SFM (Vc)	200	200	200	200	200	200	200	200	200		
						IPT (fz)	.0007	.0010	.0011	.0014	.0021	.0022	.0025	.0029			
						RPM	4070	3060	2440	2040	1530	1220	1020	760			
K		15-20	Grey cast iron	0.5D	1.5D	SFM (Vc)	370	370	370	370	370	370	370	370	370	370	
						IPT (fz)	.0010	.0014	.0016	.0019	.0026	.0032	.0037	.0042			
						RPM	7540	5650	4520	3770	2830	2260	1880	1410			
		S	31-35	Heat Resistant Super Alloys (X12 NiCrSi 36-16, 1.4864, Inconel 718, NiCr20TiAl, 2.4631, NiCu30Al, 2.4375, G-X120Mn12, 1.3401)	0.2D	1.5D	SFM (Vc)	90	90	90	90	90	90	90	90	90	90
							IPT (fz)	.0006	.0010	.0012	.0014	.0019	.0021	.0023	.0027		
							RPM	1830	1380	1100	920	690	550	460	340		
			36-37	Titanium Alloys (HB 400 Rm, HB 1050 Rm TiAl6V4, 3.7165)	0.5D	1.5D	SFM (Vc)	160	160	160	160	160	160	160	160	160	
							IPT (fz)	.0006	.0010	.0012	.0014	.0019	.0021	.0023	.0027		
							RPM	3260	2440	1960	1630	1220	980	810	610		




- NOTES:**
- ▶ Maximum recommended depth shown
 - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
 - ▶ Feed to be reduced by approximately 50% if L.O.C. (length of cut) is over 3xD
 - ▶ Reduce speed and feed recommendations for materials harder than listed
 - ▶ Recommendations above are based on ideal conditions.
- Adjust parameters accordingly for smaller taper machining centers or less rigid conditions

RECOMMENDED CUTTING CONDITIONS - INCH


EMI42, EMI43 SERIES

5 FLUTES (TitaNox Power HPC) - Side Cutting (Peel Milling)



RPM = rev./min. Feed = in./min.
Vc = ft./min. fz = in./tooth

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)								
						3/16	1/4	5/16	3/8	1/2	5/8	3/4	1	
P	1-5	Non-alloy steel	0.08D	2.0D	SFM (Vc)	650	650	650	650	650	650	650	650	650
					IPT (fz)	.0018	.0022	.0026	.0031	.0043	.0051	.0060	.0068	
					RPM	13240	9930	7950	6620	4970	3970	3310	2480	
					IPM (FEED)	119	109	103	103	107	101	99	84	
					SFM (Vc)	650	650	650	650	650	650	650	650	
	6-8	Low alloy steel	0.08D	2.0D	IPT (fz)	.0018	.0022	.0026	.0031	.0043	.0051	.0060	.0068	
					RPM	13240	9930	7950	6620	4970	3970	3310	2480	
					IPM (FEED)	119	109	103	103	107	101	99	84	
					SFM (Vc)	650	650	650	650	650	650	650	650	
					IPT (fz)	.0011	.0017	.0020	.0024	.0033	.0040	.0046	.0053	
	9	High alloyed steel, and tool steel	0.08D	2.0D	RPM	13240	9930	7950	6620	4970	3970	3310	2480	
					IPM (FEED)	73	84	80	79	82	79	76	66	
					SFM (Vc)	580	580	580	580	580	580	580	580	
					IPT (fz)	.0018	.0022	.0026	.0031	.0043	.0051	.0060	.0068	
					RPM	11820	8860	7090	5910	4430	3540	2950	2220	
10	High alloyed steel, and tool steel	0.08D	2.0D	IPM (FEED)	106	97	92	92	95	90	89	75		
				SFM (Vc)	550	550	550	550	550	550	550	550		
				IPT (fz)	.0011	.0017	.0020	.0024	.0033	.0040	.0046	.0053		
				RPM	11200	8400	6720	5600	4200	3360	2800	2100		
				IPM (FEED)	62	71	67	67	69	67	64	56		
M	12-13	Stainless steel (SUS 420, X40Cr13, 420)	0.06D	2.0D	SFM (Vc)	350	350	350	350	350	350	350	350	
					IPT (fz)	.0010	.0015	.0016	.0021	.0029	.0034	.0039	.0045	
					RPM	7130	5350	4280	3570	2670	2140	1780	1340	
					IPM (FEED)	36	40	34	37	39	36	35	30	
					SFM (Vc)	425	425	425	425	425	425	425	425	
	14.1	Stainless steel (SUS 316, 316, X5CrNiMo 17 12 2)	0.06D	2.0D	IPT (fz)	.0011	.0018	.0019	.0025	.0036	.0039	.0044	.0051	
					RPM	8660	6490	5190	4330	3250	2600	2160	1620	
					IPM (FEED)	48	58	49	54	59	51	48	41	
					SFM (Vc)	300	300	300	300	300	300	300	300	
					IPT (fz)	.0010	.0014	.0015	.0020	.0029	.0031	.0035	.0041	
	14.2	Stainless steel (SUS 630, PH 15-5)	0.06D	2.0D	RPM	6110	4580	3670	3060	2290	1830	1530	1150	
					IPM (FEED)	31	32	28	31	33	28	27	24	
					SFM (Vc)	550	550	550	550	550	550	550	550	
					IPT (fz)	.0014	.0020	.0022	.0027	.0037	.0045	.0052	.0059	
					RPM	11200	8400	6720	5600	4200	3360	2800	2100	
K	15-20	Grey cast iron	0.07D	2.0D	IPM (FEED)	78	84	74	76	78	76	73	62	
					SFM (Vc)	120	120	120	120	120	120	120	120	
					IPT (fz)	.0006	.0010	.0012	.0014	.0019	.0021	.0023	.0027	
					RPM	2440	1830	1470	1220	920	730	610	460	
					IPM (FEED)	7	9	9	9	9	8	7	6	
	31-35	Heat Resistant Super Alloys (X12NiCrSi36-16, 1.4864, Inconel 718, NiCr20TiAl, 2.4631, NiCu30Al, 2.4375, G-X120Mn12, 1.3401)	0.04D	2.0D	SFM (Vc)	300	300	300	300	300	300	300	300	
					IPT (fz)	.0006	.0010	.0012	.0014	.0019	.0021	.0023	.0027	
					RPM	6110	4580	3670	3060	2290	1830	1530	1150	
					IPM (FEED)	18	23	22	21	22	19	18	16	
					SFM (Vc)	160	160	160	160	160	160	160	160	
	36-37	Titanium Alloys (HB 400 Rm, HB 1050 Rm TiAl6V4, 3.7165)	0.05D	2.0D	IPT (fz)	.0006	.0010	.0012	.0014	.0019	.0021	.0023	.0027	
					RPM	6110	4580	3670	3060	2290	1830	1530	1150	
					IPM (FEED)	18	23	22	21	22	19	18	16	




- NOTES:**
- ▶ Maximum recommended depth shown
 - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
 - ▶ Feed to be reduced by approximately 50% if L.O.C. (length of cut) is over 3xD
 - ▶ Reduce speed and feed recommendations for materials harder than listed
 - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions

RECOMMENDED CUTTING CONDITIONS - INCH


EMI42, EMI43 SERIES

5 FLUTES (TitaNox Power HPC) - Slotting



RPM = rev./min. Feed = in./min.
Vc = ft./min. fz = in./tooth

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)							
						3/16	1/4	5/16	3/8	1/2	5/8	3/4	1
P	1-5	Non-alloy steel	1.0D	1.0D	SFM (Vc)	275	275	275	275	275	275	275	275
					IPT (fz)	.0010	.0013	.0015	.0018	.0024	.0029	.0034	.0039
					RPM	5600	4200	3360	2800	2100	1680	1400	1050
					IPM (FEED)	28	27	25	25	25	24	24	20
					SFM (Vc)	275	275	275	275	275	275	275	275
	6-8	Low alloy steel	1.0D	1.0D	IPT (fz)	.0010	.0013	.0015	.0018	.0024	.0029	.0034	.0039
					RPM	5600	4200	3360	2800	2100	1680	1400	1050
					IPM (FEED)	28	27	25	25	25	24	24	20
					SFM (Vc)	275	275	275	275	275	275	275	275
					IPT (fz)	.0006	.0010	.0011	.0014	.0019	.0023	.0026	.0030
	9	High alloyed steel, and tool steel	1.0D	1.0D	RPM	5600	4200	3360	2800	2100	1680	1400	1050
					IPM (FEED)	17	21	18	20	20	19	18	16
					SFM (Vc)	230	230	230	230	230	230	230	230
					IPT (fz)	.0010	.0013	.0015	.0018	.0024	.0029	.0034	.0039
					RPM	4690	3510	2810	2340	1760	1410	1170	880
10	High alloyed steel, and tool steel	1.0D	0.75D	IPM (FEED)	23	23	21	21	21	20	20	17	
				SFM (Vc)	250	250	250	250	250	250	250	250	
				IPT (fz)	.0006	.0010	.0011	.0014	.0019	.0023	.0026	.0030	
				RPM	5090	3820	3060	2550	1910	1530	1270	950	
				IPM (FEED)	15	19	17	18	18	18	17	14	
M	12-13	Stainless steel (SUS 420, X40Cr13, 420)	1.0D	0.5D	SFM (Vc)	225	225	225	225	225	225	225	225
					IPT (fz)	.0006	.0008	.0009	.0012	.0017	.0021	.0025	.0029
					RPM	4580	3440	2750	2290	1720	1380	1150	860
					IPM (FEED)	14	14	12	14	15	13	13	11
					SFM (Vc)	250	250	250	250	250	250	250	250
	14.1	Stainless steel (SUS 316, 316, X5CrNiMo 17 12 2)	1.0D	0.5D	IPT (fz)	.0006	.0010	.0011	.0014	.0021	.0023	.0025	.0029
					RPM	5090	3820	3060	2550	1910	1530	1270	950
					IPM (FEED)	15	19	17	18	20	18	16	14
					SFM (Vc)	200	200	200	200	200	200	200	200
					IPT (fz)	.0006	.0008	.0009	.0011	.0017	.0018	.0020	.0023
	14.2	Stainless steel (SUS 630, PH 15-5)	1.0D	0.5D	RPM	4070	3060	2440	2040	1530	1220	1020	760
					IPM (FEED)	12	12	11	11	13	11	10	9
					SFM (Vc)	260	260	260	260	260	260	260	260
					IPT (fz)	.0008	.0011	.0013	.0015	.0021	.0026	.0030	.0034
					RPM	5300	3970	3180	2650	1990	1590	1320	990
K	15-20	Grey cast iron	1.0D	1.0D	IPM (FEED)	21	22	21	20	21	21	20	17
					SFM (Vc)	64	64	64	64	64	64	64	64
					IPT (fz)	.0005	.0008	.0010	.0011	.0015	.0017	.0019	.0021
					RPM	1300	980	780	650	490	390	330	240
					IPM (FEED)	3	4	4	4	4	3	3	3
	31-35	Heat Resistant Super Alloys (X12NiCrSi36-16, 1.4864, Inconel 718, NiCr20TiAl, 2.4631, NiCu30Al, 2.4375, G-X120Mn12, 1.3401)	1.0D	0.4D	SFM (Vc)	160	160	160	160	160	160	160	160
					IPT (fz)	.0005	.0008	.0010	.0011	.0015	.0017	.0019	.0021
					RPM	3260	2440	1960	1630	1220	980	810	610
					IPM (FEED)	8	10	10	9	9	8	8	6




- NOTES:**
- ▶ Maximum recommended depth shown
 - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
 - ▶ Feed to be reduced by approximately 50% if L.O.C. (length of cut) is over 3xD
 - ▶ Reduce speed and feed recommendations for materials harder than listed
 - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions

RECOMMENDED CUTTING CONDITIONS – METRIC


GMG40 SERIES

4 FLUTES DOUBLE CORE - Side Cutting



RPM = rev./min. Feed = in./min.
Vc = ft./min. fz = in./tooth

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)							
						6.0	8.0	10.0	12.0	14.0	16.0	20.0	25.0
P	1-4	Non-alloy steel	0.4D	1.0D	SFM (Vc)	525	525	525	525	525	525	525	525
					IPT (fz)	.0011	.0014	.0017	.0021	.0023	.0025	.0030	.0033
					RPM	8490	6370	5090	4240	3640	3180	2550	2040
					IPM (FEED)	37	36	35	36	33	31	27	27
	5	Non-alloy steel	0.4D	1.0D	SFM (Vc)	490	490	490	490	490	490	490	490
					IPT (fz)	.0010	.0014	.0017	.0019	.0022	.0025	.0028	.0033
					RPM	7920	5940	4750	3960	3400	2970	2380	1900
					IPM (FEED)	32	33	32	30	30	30	27	25
	6-7	Low alloy steel	0.4D	1.0D	SFM (Vc)	525	525	525	525	525	525	525	525
					IPT (fz)	.0011	.0014	.0017	.0021	.0023	.0025	.0030	.0033
					RPM	8490	6370	5090	4240	3640	3180	2550	2040
					IPM (FEED)	37	36	35	36	33	31	27	27
8-9	Low alloy steel	0.4D	1.0D	SFM (Vc)	490	490	490	490	490	490	490	490	
				IPT (fz)	.0010	.0014	.0017	.0019	.0022	.0025	.0028	.0033	
				RPM	7920	5940	4750	3960	3400	2970	2380	1900	
				IPM (FEED)	32	33	32	30	30	30	27	25	
10-11.1	High alloyed steel, and tool steel	0.4D	1.0D	SFM (Vc)	490	490	490	490	490	490	490	490	
				IPT (fz)	.0011	.0014	.0018	.0021	.0024	.0026	.0030	.0033	
				RPM	7920	5940	4750	3960	3400	2970	2380	1900	
				IPM (FEED)	35	33	34	33	33	31	29	25	
M	12-13	Stainless steel (SUS 420, X40Cr13, 420)	0.4D	1.0D	SFM (Vc)	510	510	510	510	510	510	510	510
					IPT (fz)	.0013	.0018	.0022	.0026	.0030	.0034	.0037	.0045
					RPM	8250	6190	4950	4120	3530	3090	2470	1980
					IPM (FEED)	43	45	44	43	42	42	37	36
	14.1	Stainless steel (SUS 316, 316L, X5CrNiMo 17 12 2)	0.4D	1.0D	SFM (Vc)	345	345	345	345	345	345	345	345
					IPT (fz)	.0010	.0013	.0016	.0019	.0022	.0024	.0028	.0032
					RPM	5580	4180	3350	2790	2390	2090	1670	1340
					IPM (FEED)	22	22	21	21	21	20	19	17
	14.2	Stainless steel (SUS 630, PH 15-5)	0.4D	0.6D	SFM (Vc)	145	145	145	145	145	145	145	145
					IPT (fz)	.0006	.0008	.0010	.0013	.0014	.0016	.0018	.0021
					RPM	2340	1760	1410	1170	1000	880	700	560
					IPM (FEED)	6	6	6	6	6	6	5	5
K	15-20	Grey cast iron	0.4D	1.0D	SFM (Vc)	575	575	575	575	575	575	575	575
					IPT (fz)	.0008	.0011	.0014	.0017	.0019	.0021	.0024	.0028
					RPM	9300	6970	5580	4650	3980	3490	2790	2230
					IPM (FEED)	30	31	31	32	30	29	27	25
S	31-35	Heat Resistant Super Alloys (X12 NiCrSi 36-16, 1.4864, Inconel 718, NiCr20TiAl, 2.4631, NiCu30Al, 2.4375, G-X120Mn12, 1.3401)	0.3D	0.6D	SFM (Vc)	105	105	105	105	105	105	105	105
					IPT (fz)	.0008	.0010	.0013	.0015	.0017	.0019	.0022	.0026
					RPM	1700	1270	1020	850	730	640	510	410
					IPM (FEED)	5	5	5	5	5	4	4	4
	36-37	Titanium Alloys (HB 400 Rm, HB 1050 Rm TiAl6V4, 3.7165)	0.3D	0.6D	SFM (Vc)	230	230	230	230	230	230	230	230
					IPT (fz)	.0013	.0019	.0022	.0026	.0030	.0034	.0037	.0045
					RPM	3720	2790	2230	1860	1590	1390	1120	890
					IPM (FEED)	19	21	20	19	19	17	16	16




- NOTES:**
- ▶ Maximum recommended depth shown
 - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
 - ▶ Feed to be reduced by approximately 50% if L.O.C. (length of cut) is over 3xD
 - ▶ Reduce speed and feed recommendations for materials harder than listed
 - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions

RECOMMENDED CUTTING CONDITIONS – METRIC


GMG40 SERIES

4 FLUTES DOUBLE CORE - Slotting



RPM = rev./min. Feed = in./min.
Vc = ft./min. fz = in./tooth

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)							
						6.0	8.0	10.0	12.0	14.0	16.0	20.0	25.0
P	1-4	Non-alloy steel	1.0D	1.0D	SFM (Vc)	410	410	410	410	410	410	410	410
					IPT (fz)	.0010	.0013	.0017	.0019	.0022	.0025	.0028	.0033
					RPM	6630	4970	3980	3310	2840	2490	1990	1590
					IPM (FEED)	27	26	27	25	25	25	22	21
	5	Non-alloy steel	1.0D	1.0D	SFM (Vc)	395	395	395	395	395	395	395	395
					IPT (fz)	.0010	.0013	.0017	.0019	.0022	.0025	.0028	.0033
					RPM	6390	4790	3830	3190	2740	2400	1920	1530
					IPM (FEED)	26	25	26	24	24	24	22	18
	6-7	Low alloy steel	1.0D	1.0D	SFM (Vc)	410	410	410	410	410	410	410	410
					IPT (fz)	.0010	.0013	.0017	.0019	.0022	.0025	.0028	.0033
					RPM	6630	4970	3980	3310	2840	2490	1990	1590
					IPM (FEED)	27	26	27	25	25	25	22	21
8-9	Low alloy steel	1.0D	1.0D	SFM (Vc)	395	395	395	395	395	395	395	395	
				IPT (fz)	.0010	.0013	.0017	.0019	.0022	.0025	.0028	.0033	
				RPM	6390	4790	3830	3190	2740	2400	1920	1530	
				IPM (FEED)	26	25	26	24	24	24	22	18	
10-11.1	High alloyed steel, and tool steel	1.0D	1.0D	SFM (Vc)	395	395	395	395	395	395	395	395	
				IPT (fz)	.0011	.0014	.0017	.0021	.0023	.0025	.0030	.0033	
				RPM	6390	4790	3830	3190	2740	2400	1920	1530	
				IPM (FEED)	28	27	26	27	25	24	23	20	
M	12-13	Stainless steel (SUS 420, X40Cr13, 420)	1.0D	1.0D	SFM (Vc)	410	410	410	410	410	410	410	410
					IPT (fz)	.0013	.0018	.0022	.0026	.0030	.0034	.0037	.0045
					RPM	6630	4970	3980	3310	2840	2490	1990	1590
					IPM (FEED)	34	36	35	34	33	32	29	26
	14.1	Stainless steel (SUS 316, 316L, X5CrNiMo 17 12 2)	1.0D	1.0D	SFM (Vc)	280	280	280	280	280	280	280	280
					IPT (fz)	.0010	.0013	.0016	.0019	.0022	.0024	.0028	.0032
					RPM	4530	3400	2720	2260	1940	1700	1360	1090
					IPM (FEED)	18	18	17	17	17	16	15	14
	14.2	Stainless steel (SUS 630, PH 15-5)	1.0D	0.5D	SFM (Vc)	120	120	120	120	120	120	120	120
					IPT (fz)	.0006	.0008	.0010	.0013	.0014	.0016	.0018	.0021
					RPM	1940	1460	1160	970	830	730	580	470
					IPM (FEED)	5	5	5	5	5	5	4	4
K	15-20	Grey cast iron	1.0D	1.0D	SFM (Vc)	460	460	460	460	460	460	460	460
					IPT (fz)	.0008	.0011	.0014	.0017	.0019	.0021	.0024	.0026
					RPM	7440	5580	4460	3720	3190	2790	2230	1790
					IPM (FEED)	24	25	25	25	24	23	21	19
S	31-35	Heat Resistant Super Alloys (X12 NiCrSi 36-16, 1.4864, Inconel 718, NiCr20TiAl, 2.4631, NiCu30Al, 2.4375, G-X120Mn12, 1.3401)	1.0D	0.4D	SFM (Vc)	80	80	80	80	80	80	80	80
					IPT (fz)	.0007	.0009	.0012	.0014	.0016	.0017	.0020	.0022
					RPM	1290	970	780	650	550	490	390	310
					IPM (FEED)	4	3	4	4	4	3	3	3
	36-37	Titanium Alloys (HB 400 Rm, HB 1050 Rm TiAl6V4, 3.7165)	1.0D	1.0D	SFM (Vc)	180	180	180	180	180	180	180	180
					IPT (fz)	.0013	.0018	.0022	.0026	.0030	.0034	.0037	.0045
					RPM	2910	2180	1750	1460	1250	1090	870	700
					IPM (FEED)	15	16	15	15	15	15	13	11



- NOTES:**
- ▶ Maximum recommended depth shown
 - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
 - ▶ Feed to be reduced by approximately 50% if L.O.C. (length of cut) is over 3xD
 - ▶ Reduce speed and feed recommendations for materials harder than listed
 - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions

RECOMMENDED CUTTING CONDITIONS – METRIC


GMG24, GMG26, GMG28, GMG30 SERIES

5 FLUTES - Side Cutting



RPM = rev./min. Feed = in./min.
Vc = ft./min. fz = in./tooth

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)								
						6.0	8.0	10.0	12.0	14.0	16.0	18.0	20.0	25.0
P	1-4	Non-alloy steel	0.3D	1.5D	SFM (Vc)	475	475	475	475	475	475	475	475	475
					IPT (fz)	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040
					RPM	7680	5760	4610	3840	3290	2880	2560	2300	1840
					IPM (FEED)	50	43	46	48	44	43	42	40	37
	5	Non-alloy steel	0.3D	1.5D	SFM (Vc)	330	330	330	330	330	330	330	330	330
					IPT (fz)	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040
					RPM	5340	4000	3200	2670	2290	2000	1780	1600	1280
					IPM (FEED)	35	30	32	33	31	30	29	28	26
	6-7	Low alloy steel	0.3D	1.5D	SFM (Vc)	475	475	475	475	475	475	475	475	475
					IPT (fz)	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040
					RPM	7680	5760	4610	3840	3290	2880	2560	2300	1840
					IPM (FEED)	50	43	46	48	44	43	42	40	37
8-9	Low alloy steel	0.3D	1.5D	SFM (Vc)	330	330	330	330	330	330	330	330	330	
				IPT (fz)	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040	
				RPM	5340	4000	3200	2670	2290	2000	1780	1600	1280	
				IPM (FEED)	35	30	32	33	31	30	29	28	26	
10-11.1	High alloyed steel, and tool steel	0.3D	1.5D	SFM (Vc)	200	200	200	200	200	200	200	200	200	
				IPT (fz)	.0009	.0011	.0014	.0017	.0019	.0021	.0023	.0024	.0028	
				RPM	3230	2430	1940	1620	1390	1210	1080	970	780	
				IPM (FEED)	15	13	14	14	13	13	12	12	11	
M	12-13	Stainless steel (SUS 420, X40Cr13, 420)	0.3D	1.5D	SFM (Vc)	385	385	385	385	385	385	385	385	385
					IPT (fz)	.0009	.0010	.0012	.0018	.0020	.0021	.0022	.0024	.0028
					RPM	6230	4670	3740	3110	2670	2330	2080	1870	1490
					IPM (FEED)	28	23	22	28	27	24	23	22	21
	14.1	Stainless steel (SUS 316, 316L, X5CrNiMo 17 12 2)	0.3D	1.5D	SFM (Vc)	270	270	270	270	270	270	270	270	270
					IPT (fz)	.0012	.0013	.0015	.0025	.0026	.0027	.0028	.0030	.0035
					RPM	4370	3270	2620	2180	1870	1640	1460	1310	1050
					IPM (FEED)	26	21	20	27	24	22	20	20	18
	14.2	Stainless steel (SUS 630, PH 15-5)	0.3D	1.5D	SFM (Vc)	195	195	195	195	195	195	195	195	195
					IPT (fz)	.0012	.0013	.0015	.0025	.0026	.0027	.0028	.0030	.0035
					RPM	3150	2360	1890	1580	1350	1180	1050	950	760
					IPM (FEED)	19	15	14	20	18	16	15	14	13
K	15-20	Grey cast iron	0.3D	1.5D	SFM (Vc)	350	350	350	350	350	350	350	350	350
					IPT (fz)	.0017	.0019	.0025	.0031	.0034	.0038	.0041	.0044	.0050
					RPM	5660	4240	3400	2830	2430	2120	1890	1700	1360
					IPM (FEED)	48	40	43	44	41	40	39	37	34
S	31-35	Heat Resistant Super Alloys (X12 NiCrSi 36-16, 1.4864, Inconel 718, NiCr20TiAl, 2.4631, NiCu30Al, 2.4375, G-X120Mn12, 1.3401)	0.1D	1.5D	SFM (Vc)	100	100	100	100	100	100	100	100	100
					IPT (fz)	.0008	.0009	.0011	.0017	.0018	.0019	.0019	.0021	.0024
					RPM	1620	1210	970	810	690	610	540	490	390
					IPM (FEED)	6	5	5	7	6	6	5	5	5
	36-37	Titanium Alloys (HB 400 Rm, HB 1050 Rm TiAl6V4, 3.7165)	0.3D	1.5D	SFM (Vc)	225	225	225	225	225	225	225	225	225
					IPT (fz)	.0011	.0011	.0013	.0022	.0023	.0024	.0025	.0027	.0031
					RPM	3640	2730	2180	1820	1560	1360	1210	1090	870
					IPM (FEED)	20	15	14	20	18	16	15	15	13



- NOTES:**
- ▶ Maximum recommended depth shown
 - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
 - ▶ Feed to be reduced by approximately 50% if L.O.C. (length of cut) is over 3xD
 - ▶ Reduce speed and feed recommendations for materials harder than listed
 - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions

HIGH QUALITY PRODUCTS and ON TIME DELIVERY for WORLD-WIDE CUSTOMERS

Since 1982, YG-1 has been committed to quality, innovation and the unique customer experience. Our performance and experience have granted YG-1 the global impression of one of the leading manufacturers of high quality cutting tool solutions. This global footprint expands over 75 countries, with international logistic centers, pledging to our customers to give the best service available today - and tomorrow.

EUROPE



ASIA PACIFIC



AMERICAS



AFRICA



YG-1 CO., LTD.

* For the more information on sales network, please contact the head office as below;

YG-1 HEAD OFFICE

13-40, Songdogwahak-ro 16beon-gil,
Yeonsu-gu, Incheon 21984, South Korea
Phone: +82-32-526-0909
www.yg1.kr / yg1@yg1.kr


YG-1 USA

730 Corporate Woods Parkway
Vernon Hills, IL 60061 U.S.A.
Phone: 800-765-8665 / Technical Assistance: 888-868-5988
www.yg1usa.com

TAKE IT ON WITH



HIGH-PERFORMANCE MACHINING MADE EASY.



Scan this QR code to see our
TitaNox tools at work.

YG YG-1 CO., LTD.

YG-1 USA

730 Corporate Woods Parkway
Vernon Hills, IL 60061 U.S.A.

Phone: 800-765-8665

Technical Assistance: 888-868-5988

www.yg1usa.com

YG-1 CANADA INC.

3375 North Service Road, Unit A8
Burlington, Ontario, CANADA L7N 3G2

Phone: +1 905-335-2500

FAX: +1 905-335-4003

Customer Service: orders@yg1.ca

www.yg1.ca

YG-1 TOOLS MEXICO SA DE CV

A Carretera Estatal 200 Queretaro-Tequisquiapan KM 19+530 Parque Industrial
Advance Modulo 4 Edif A, Navajas, El Marques, Querétaro, México CP 76260

Phone: +52 442 348 12 70

Customer Service: ventas@yg1mexico.com

www.yg1mexico.com

HEAD OFFICE

13-40, Songdogwahak-ro 16beon-gil,
Yeonsu-gu, Incheon 21984, South Korea

Notice YG-1 Global head office is relocating from December 2020 to a new address as above;

Phone: +82-32-526-0909

www.yg1.kr

E-mail: yg1@yg1.kr



Search 'YG-1' on social media outlets



YG1YUTP210830003